



An der Glinder Au 6
D-22115 Hamburg

Tel: +49 40 7121045

Fax: +49 40 7135871

Email: contact@micamills.de

Product Information

Talc 0000 / FM 20

Customs tariff code: 25 26 20 000
CAS – Number: 14807 – 96 – 6

Typical chemical analysis	SiO ₂	36,9 %
	MgO	28,5 %
	Al ₂ O ₃	1,1 %
	CaO	7,3 %
	MnO	0,1 %
	TiO ₂	0,05 %

Typical properties	Loss of ignition 1000°C	20,0 %
	pH value	8,3
	Whiteness	69 – 72 %
	Specific gravity	2,8 g / cm ³
	Oil absorption	32 – 34
	Hardness MOHS	1

Typical screen analysis	45 µm sieve	< 25 %
-------------------------	-------------	--------