



An der Glinder Au 6  
D-22115 Hamburg

Tel: +49 40 7121045

Fax: +49 40 7135871

e-mail: [contact@micamills.de](mailto:contact@micamills.de)

## Product Information

### Mica 20/30 0,2 – 5 mm

Muscovite mica formula:  $K_2Al_4(Al_2Si_6O_{20})(OH)_4$

Customs tariff code: 25 25 20 000  
CAS – Number: 12001 – 26 - 2

Typical chemical analysis:

SiO <sub>2</sub>	45 - 48 %
Fe <sub>2</sub> O <sub>3</sub>	2 - 5 %
Al <sub>2</sub> O <sub>3</sub>	33 - 37 %
K <sub>2</sub> O	9 - 11 %

Properties:

Bulk density	150 – 200 kg / m <sup>3</sup>
Solubility in water	insoluble
Explosion limits	inert
Thermal decomposition	does not occur
Toxicity	non toxic

Typical screen analysis:

+ 5.000 micron	0 %
+ 2.000 micron	< 15 %
+ 1.000 micron	20 – 40 %
+ 500 micron	20 – 40 %
- 500 micron	20 – 45 %